COMMERCIAL TESTING COMPANY
1215 South Hamilton Street • Dalton, Georgia 30720
Telephone (706) 278–3935 • Facsimile (706) 278–3936

Report Number 25–03132

Arte nv
Industriezone 'De Waerde'
Senator A. Jeurissenlaan 1210
3520 Zonhoven, Belgium

Test Number 5603–6782B–R
September 17, 2020

Washability

Test Method: The material was tested in accordance with ASTM International standard classification F793/F793M–15, *Wall Covering by Use Characteristics*, which covers the classification of wall covering according to its serviceability in use. A sample from an area with as many different printed colors as possible, as well as the ground, is tested in a Gardner washability machine equipped with a WG-2000C cellulose sponge saturated with the specified detergent solution. At the end of the requisite number of cycles, the machine is stopped, the specimen removed, and rinsed under running water. After drying, the specimen shall show no evidence of appreciable damage to the printed or ground surface. Areas of localized wear clearly related to wrinkles is ignored.

Material Tested: The client submitted a sample of paper backed vinyl wallcovering identified as **Textura Puro**.

Test Data: The client requested the sample be exposed to 100 cycles, the requisite number for a Type II classification.

Test Result: The material tested, **Textura Puro**, meets Type II requirements for washability in accordance with ASTM F793/F793M–15. Overall classification can not be based on a single performance property.

Commercial Testing Company

Deviane Jackson

(Authorized Signature)

TEST REPORT REVISION LOG

NUMBER	DATE	PAGES	REVISION
0	09/17/20	1 OF 1	*Issuance of Original Report*
1	03/21/25	1 OF 1	*Identification revised from original* **Figura** *to* **Textura Puro**. *New Report number issued replacing original* **20–09158R**. *Letter certifying change filed with original test request and report.*

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced standard, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.